



## CLOUD 9 SILVER WOODLAY

- CLOUD 9 APT CRUMB
- DESIGNED FOR USE UNDER WOODEN FLOORS
- UNIQUE MOISTURE LOCK SYSTEM
- IMPACT SOUND REDUCTION PROPERTIES

### RECOMMENDED AREAS OF USE

SUITABLE FOR SOLID AND LAMINATE WOOD FLOORS. SUPPORTS FLOOR GIVING A MORE COMFORTABLE FEEL. NOT TO BE USED AS A REPLACEMENT FOR DPM.

Manufactured in the UK to BS 5808:1991 & BS EN 14499:2015

### STANDARD SPECIFICATIONS


TOP SURFACE	Silver coloured metalised film	
BOTTOM SURFACE	Corona treated polymer film	
NOMINAL THICKNESS	3.00 mm	
NOMINAL ROLL WEIGHT	8.1 Kg	17.9 lb
WEIGHT PER UNIT AREA	537 g/M <sup>2</sup>	16 oz/yd <sup>2</sup>
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial carpet installation (when used in recommended areas)	
CORE DENSITY	160 Kg/M <sup>3</sup>	
PRODUCT DENSITY	180 Kg/M <sup>3</sup>	

### BS. 5808 : 1991 TEST RESULTS - BRITISH STANDARD FOR CARPET UNDERLAYS

END USE CLASSIFICATION	BS.5808	N/A
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS.4098	>50 J/m <sup>2</sup>
RETENTION OF WORK OF COMPRESSION	BS.4098	>90 %
LOSS IN THICKNESS AFTER STATIC LOADING	BS.4939	<5.00 %
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS.4052	<5.00 %
RESISTANCE TO CRACKING	BS.5808 (A)	Pass

### INDOOR AIR QUALITY TEST

TESTED TO ISO16000		
FRENCH VOC EMISSION CLASS LABEL	A+	



### OTHER RELEVANT TESTS

THERMAL RESISTANCE (TOG RATING)	BS 4745	0.9 TOG
IMPACT SOUND IMPROVEMENT INDEX (Test/Rated to BS EN ISO 140-8 / BS EN ISO 717-2)		21 dB

ISSUE 4 29 -AUG-14

#### DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.

